

Antique (AQ)

Upholstery Leather Technical Data**Leather Specifications**

| | |
|--------------------|---------------------------------------|
| Style: | Antique (AQ) |
| Description: | Enhanced grain, aniline dyed leather |
| Thickness: | 0.9–1.0 mm |
| Weight: | 2.25–2.50 oz. per sq. ft. |
| Average Hide Size: | 50–55 sq. ft. |
| Finish: | Durable, breathable protective finish |

Performance Characteristics**Tests**

| | |
|--|--------------------------------|
| Light Fastness (AATCC Method 16, Option E, 72 Hours) | Class 4 |
| Crocking (ASTM D-5053): | Dry: Class 4-5 Wet: Class 4 |
| Abrasion (ASTM D-3884): | 1,000+ cycles (CS-10 wheels) |
| Flex (ASTM D-2097): | 70,000 cycles |
| Tearing Strength, Double Hole (ASTM D-4705): | 25 lbs. |
| Breaking Force (ASTM D-2208): | 150 lbs. |
| Elongation (ASTM D-2211): | 40-60% at 50 lbs. |

Flammability*Passes the following flammability tests*

| | |
|---|---|
| California Technical Bulletin 117 | Complies |
| Boston Fire Dept. BFD IX-1 | Complies (with flame treatment) |
| Cigarette Ignition Resistance (NFPA-260) | Class I |
| Surface Burning Characteristics of Bldg. Materials (ASTM E84) | Class II (Class I with flame treatment) |
| IMO Resolution A.652 (16) | Complies |
| IMO Resolution A.653 (16) | Complies |

*Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent.

Recommended Cleaning Instructions

Dust regularly. Minor spots can be washed off using lukewarm water and mild soap.

Do not soak. Never clean with abrasive solvents, alcohol, or wax-based products.

Approved maintenance products are available from Spinneybeck.