

Alaska

Upholstery Leather

spinneybeck




**Alaska is as
pretty as a pearl.**

The pearlized surface of Alaska creates an iridescence reminiscent of glistening snow. Alaska is produced from the finest and clearest bovine raw material obtained exclusively from the Piedmont and Tuscany regions of northern Italy. These regions provide some of the world's finest selection of raw material available only in limited quantities. A special retannage completes the enrichment process of the leather, providing a smooth tight grain and suppleness of hand. The final finish application contains finely milled mother of pearl, giving Alaska a deep, rich, luminescent finish not found in other pearlized leathers. Alaska also features a breathable protective finish, which is impregnated into the leather, becoming an integral part of the material.

Product	Alaska (AL)
Content	European cowhide
Origin	Italy
Hide Size	50–55 sq ft (4.6–5.1 sq m)
Thickness	0.9–1.0 mm
Weight	2.25–2.5 oz / sq ft (687–763 g / sq m)
Grain	Full
Grain Texture	Smooth, tight
Tannage	Chrome
Dye	Aniline
Finish	Pearlized
Primary Uses	Upholstery, handrails, wall panels, architectural applications
Industry	Automotive, aviation, contract, hospitality, marine, residential
Maintenance	Wipe with a cool, damp cloth. For tougher soiling, use a pH-balanced soap and rinse. Repeat, if needed. Occasional use of Spinneybeck Finished Leather Cleaner, Conditioner & Protector is recommended. Other leather cleaners such as saddle soap or household cleaners that may contain harsh chemicals, alcohol or ink removers should never be used.
Custom	Custom colors not available
Special Services	Flame treatment and perforated available with an upcharge
Colorfastness to Light	Class 4
Colorfastness to Crocking	Class 4–5 (dry), Class 4 (wet)
Flammability	ASTM E 84: Class A (flame treated) Boston Fire Dept BFD IX-1: Pass (flame treated) BS EN1021 (Part I and Part II): Pass BS 5852 Crib 5 and Crib 7: Pass (flame treated) CAL 117: Pass CAL 133: Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent (flame treated) Cigarette Ignition Resistance NFPA 260: Class 1 FAR 25.853(a) 60 sec vertical burn, 12 sec vertical burn. Oil burner-fire block: Pass IMO Resolution A.652 (16): Pass IMO Resolution A.653(16) Part 2 and 5: Pass (flame treated) NF P 95 512 1986 (Electric Burner Test): Class M1 (flame treated)
Durability + Strength	Abrasion ASTM D 7255: 1,000+ cycles (CS-10 wheels) Breaking Force ASTM D 2208: 150 lb Elongation ASTM D 2211: 30–50% at 50 lb Flex ASTM D 2097: 70,000 flexes Tearing Strength ASTM D 4705: 25 lb


Standard Colors



AL 5039



AL 5036



AL 5007



AL 5034



AL 5004



AL 5015



AL 5047



AL 5050



AL 5019



AL 5049



AL 5037



AL 5023



AL 5022



AL 5027



AL 5025



AL 5024



AL 5026



AL 5044



AL 5029



AL 5014



AL 5028



AL 5006



AL 0411



AL 5013