



**Andes**  
Upholstery Leather

spinneybeck

# About

---



Andes is a natural, chromium tanned, aniline dyed, upholstery leather with a lightly enhanced grain texture. The selection of hides used to produce Andes originates from northern Italy, southern Germany, and Switzerland. The light enhancement process refines the surface of the leather without penetrating the dermis of the hide. The combination of the lightweight material, refined enhanced grain texture, and special ironing process contribute to its suppleness and smoothness. This enhanced grain leather closely approximates the luxurious hand of Sabrina for price-sensitive projects.



# Specifications


<b>Name</b>	Andes (AD)
<b>Content</b>	European cowhide
<b>Origin</b>	Italy
<b>Hide Size</b>	55–65 ft <sup>2</sup> (5.1–6.0 m <sup>2</sup> )
<b>Thickness</b>	1.0–1.1 mm
<b>Weight</b>	2.5–2.75 oz / ft <sup>2</sup> (763–839 g / m <sup>2</sup> )
<b>Grain</b>	Enhanced
<b>Grain Texture</b>	Slightly pronounced
<b>Tannage</b>	Chrome
<b>Dye</b>	Aniline
<b>Finish</b>	Medium
<b>Primary Uses</b>	Upholstery, handrails, rugs, wall panels, architectural applications
<b>Industry</b>	Automotive, aviation, contract, hospitality, marine, residential
<b>Maintenance</b>	Wipe with a cool, damp cloth. For tougher soiling, use a pH-balanced soap and rinse. Repeat, if needed. Occasional use of Spinneybeck Finished Leather Cleaner, Conditioner & Protector or Finished Leather Maintenance Kit is recommended. Other leather cleaners such as saddle soap or household cleaners that may contain harsh chemicals, alcohol or ink removers should never be used.
<b>Custom</b>	Custom colors available
<b>Special Services</b>	Flame treatment and perforated available with an upcharge
<b>Colorfastness to Light</b>	Class 4
<b>Colorfastness to Crocking</b>	Class 4–5 (dry), Class 4 (wet)
<b>Flammability</b>	ASTM E 84: Class A (flame treated) Boston Fire Dept BFD IX-1: Pass (flame treated) BS EN1021 (Part I and Part II): Pass BS 5852 Crib 5 and Crib 7: Pass (flame treated) CAL 117: Pass CAL 133: Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent (flame treated) Cigarette Ignition Resistance NFPA 260: Class 1 FAR 25.853(a) 60 sec vertical burn, 12 sec vertical burn. Oil burner-fire block: Pass IMO Resolution A.653(16) Part 2 and 5: Pass (flame treated) NF P 95 512 1986 (Electric Burner Test): Class M1 (flame treated), Class M2 (flame treated)
<b>Durability + Strength</b>	Abrasion ASTM D 7255: 1,000+ cycles (CS-10 wheels) Breaking Force ASTM D 2208: 150 lb Elongation ASTM D 2211: 30–50% at 50 lb Flex ASTM D 2097: 70,000 flexes Tearing Strength ASTM D 4705: 25 lb

# Standard Colors

---



AD 6021



AD 6020



AD 6024



AD 6048



AD 6062



AD 6049



AD 6030



AD 6064




AD 6019



AD 6028



AD 6027



AD 6053



AD 6047



AD 6065



AD 6033



AD 6052



AD 6022




AD 6045




AD 6063




AD 6059




AD 6061



AD 6025



AD 6023



AD 6036




AD 6012




AD 6040




AD 6035




AD 6054




AD 6034




AD 6051




AD 6055




AD 6006




AD 6016



AD 6001



AD 6007



AD 6018

# Standard Colors

---



AD 6003



AD 6008



AD 6011



AD 6009



AD 6010



AD 6032



AD 6013



AD 6057




AD 6043



AD 6038



AD 6037



AD 6026