

# Derby

Upholstery Leather

spinneybeck



## Derby is a luxurious, raised grain leather.


Derby is made from the finest and clearest bovine material. The premium, select hides used to produce Derby are obtained exclusively from the Piedmont and Tuscany regions of northern Italy. The vegetable combination retannage creates the luxurious, raised grain texture and robust roundness of hand. This clear leather reveals its natural characteristics while retaining high performance, aging beautifully and creating a fine patina. The high quality dyes allow a greater saturation and dye enrichment than ordinary upholstery leathers. Derby features a breathable protective finish which is impregnated into the leather, becoming an integral part of the material, and protects the surface while keeping the user cool.

<b>Product</b>	Derby (DE)
<b>Content</b>	European cowhide
<b>Origin</b>	Italy
<b>Hide Size</b>	55–60 sq ft (5.1–5.6 sq m)
<b>Thickness</b>	1.4–1.6 mm
<b>Weight</b>	3.5–4.0 oz / sq ft (1068–1221 g / sq m)
<b>Grain</b>	Full
<b>Grain Texture</b>	Raised
<b>Tannage</b>	Combination
<b>Dye</b>	Aniline
<b>Finish</b>	Medium
<b>Primary Uses</b>	Upholstery, handrails, wall panels, architectural applications
<b>Industry</b>	Automotive, aviation, contract, hospitality, marine, residential
<b>Maintenance</b>	Wipe with a cool, damp cloth. For tougher soiling, use a pH-balanced soap and rinse. Repeat, if needed. Occasional use of water-based leather cleaner, conditioner, and protector is recommended. Other leather cleaners such as saddle soap or household cleaners that may contain harsh chemicals, alcohol or ink removers should never be used.
<b>Custom</b>	Custom colors available
<b>Special Services</b>	Flame treatment, perforated, and embossed available with an upcharge
<b>Colorfastness to Light</b>	Class 4
<b>Colorfastness to Crocking</b>	Class 4 (dry), Class 3 (wet)
<b>Flammability</b>	ASTM E 84: Class A (flame treated) Boston Fire Dept BFD IX-1: Pass (flame treated) BS EN1021 (Part I and Part II): Pass BS 5852 Crib 5 and Crib 7: Pass (flame treated) CAL 117: Pass CAL 133: Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent (flame treated) Cigarette Ignition Resistance NFPA 260: Class 1 FAR 25.853(a) 60 sec vertical burn, 12 sec vertical burn. Oil burner-fire block: Pass IMO Resolution A.652 (16): Pass IMO Resolution A.653(16) Part 2 and 5: Pass (flame treated) NF P 95 512 1986 (Electric Burner Test): Class M1 (flame treated)
<b>Durability + Strength</b>	Abrasion ASTM D 7255: n/a Breaking Force ASTM D 2208: 250 lb Breaking Force ASTM D 2208: 300 lb Elongation ASTM D 2211: 30–50% at 50 lb Flex ASTM D 2097: 70,000 flexes Tearing Strength ASTM D 4705: 50 lb


#### Standard Colors




DE 0238




DE 0204




DE 0206



DE 0231



DE 0230



DE 0234



DE COAL