

España

Upholstery Leather

spinneybeck



España is a supple, enhanced grain leather.

España is a select chromium tanned, aniline dyed, enhanced grain upholstery leather. The select lower Alpine hides required to produce España are derived from northern Italy, southern Germany, and Switzerland. The special retannage of España adds to the enrichment of the leather and provides a smooth, tight grain and suppleness of hand which approximates our Sabrina, a favorite of clients seeking a multi-purpose, high performance leather. The recipes used to produce España are essentially the same as those used in the production of Sabrina.

Product	España (ES)
Content	European cowhide
Origin	Italy
Hide Size	50–55 sq ft (4.6–5.1 sq m)
Thickness	0.9–1.0 mm
Weight	2.25–2.5 oz / sq ft (687–763 g / sq m)
Grain	Enhanced
Grain Texture	Smooth, tight
Tannage	Chrome
Dye	Aniline
Finish	Medium
Primary Uses	Upholstery, handrails, rugs, wall panels, architectural applications
Industry	Automotive, contract, healthcare, hospitality, marine, residential
Maintenance	Wipe with a cool, damp cloth. For tougher soiling, use a pH-balanced soap and rinse. Repeat, if needed. Occasional use of water-based leather cleaner, conditioner, and protector is recommended. Other leather cleaners such as saddle soap or household cleaners that may contain harsh chemicals, alcohol or ink removers should never be used.
Custom	Custom colors available
Special Services	Flame treatment and perforated available with an upcharge
Colorfastness to Light	Class 4
Colorfastness to Crocking	Class 4–5 (dry), Class 4 (wet)
Flammability	ASTM E 84: Class A (flame treated) Boston Fire Dept BFD IX-1: Pass (flame treated) BS EN1021 (Part I and Part II): Pass BS 5852 Crib 5 and Crib 7: Pass (flame treated) CAL 117: Pass CAL 133: Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent (flame treated) Cigarette Ignition Resistance NFPA 260: Class 1 FAR 25.853(a) 60 sec vertical burn, 12 sec vertical burn. Oil burner-fire block: Pass IMO Resolution A.652 (16): Pass IMO Resolution A.653 (16) Part 2 and 5: Pass (flame treated) NF P 95 512 1986 (Electric Burner Test): Class M1 (flame treated)
Durability + Strength	Abrasion ASTM D 7255: 1,000+ cycles (CS-10 wheels) Breaking Force ASTM D 2208: 150 lb Elongation ASTM D 2211: 30–50% at 50 lb Flex ASTM D 2097: 70,000 flexes Tearing Strength ASTM D 4705: 25 lb

Standard Colors

