



Portofino
Upholstery Leather

spinneybeck

About



Portofino is a full grain, aniline dyed leather with a full, round hand complemented by a very pronounced pebble grain texture and breathable, light protective finish. Portofino is produced from a premium selection of European raw material. The unique tannage and prolonged milling process provide an enlarged grain texture comparable to heavy weight leathers. The suppleness of Portofino is unmatched by any other leather in its class and the demand for very pronounced grain leathers inspired the creation of Portofino. The suppleness and workable texture allows for various applications that were once never considered.



Specifications

Name	Portofino (PT)
Content	European cowhide
Origin	Italy
Hide Size	50–55 ft ² (4.6–5.1 m ²)
Thickness	1.6–1.7 mm
Weight	4.0–4.25 oz / ft ² (1221–1297 g / m ²)
Grain	Full
Grain Texture	Pronounced + raised
Tannage	Chrome
Dye	Aniline
Finish	Light
Primary Uses	Upholstery, handrails, rugs, wall panels, architectural applications
Industry	Automotive, aviation, contract, hospitality, marine, residential
Maintenance	Wipe with a cool, damp cloth. For tougher soiling, use a pH-balanced soap and rinse. Repeat, if needed. Occasional use of Spinneybeck Finished Leather Cleaner, Conditioner & Protector or Finished Leather Maintenance Kit is recommended. Other leather cleaners such as saddle soap or household cleaners that may contain harsh chemicals, alcohol or ink removers should never be used.
Custom	Custom colors available
Special Services	Flame treatment, perforated and embossed available with an upcharge
Colorfastness to Light	Class 4
Colorfastness to Crocking	Class 4–5 (dry), Class 4 (wet)
Flammability	ASTM E 84: Class A (flame treated) Boston Fire Dept BFD IX-1: Pass (flame treated) BS EN1021 (Part I and Part II): Pass BS 5852 Crib 5 and Crib 7: Pass (flame treated) CAL 117: Pass CAL 133: Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent (flame treated) Cigarette Ignition Resistance NFPA 260: Class 1 FAR 25.853(a) 60 sec vertical burn, 12 sec vertical burn. Oil burner-fire block: Pass IMO Resolution A.652 (16): Pass IMO Resolution A.653(16) Part 2 and 5: Pass (flame treated) NF P 95 512 1986 (Electric Burner Test): Class M1 (flame treated), Class M2 (flame treated)
Durability + Strength	Abrasion ASTM D 7255: n/a Breaking Force ASTM D 2208: 500 lb Elongation ASTM D 2211: 30–50% at 50 lb Flex ASTM D 2097: 70,000+ flexes Tearing Strength ASTM D 4705: 40 lb


Standard Colors



PT 2310




PT 2313



PT 2315




PT 2311



PT 2312



PT 2308




PT 2307



PT 2303



PT 2302



PT 2304



PT 2305




PT 2318



PT 2320



PT 2319



PT 2301



PT 2316



PT 2317



PT BLCK