


# Saddle

Upholstery Leather

spinneybeck





**Saddle combines  
luxury hand with  
workhorse durability.**

Saddle is a full grain, aniline dyed upholstery leather. Inspired by the vegetable tanned leather used for saddlery, Saddle is produced from some of the world's finest and clearest bovine material and is a chromium-tanned leather containing a 100 percent vegetable retannage. The premium, select hides required to produce Saddle originate from Scandinavian countries. The special retannage and ironing combine to produce a fine, tight-grained leather which makes Saddle a favorite of leather aficionados everywhere.

<b>Product</b>	Saddle (SL)
<b>Content</b>	European cowhide
<b>Origin</b>	Italy
<b>Hide Size</b>	55–65 sq ft (5.1–6.0 sq m)
<b>Thickness</b>	1.0–1.2 mm
<b>Weight</b>	2.5–3.0 oz / sq ft (763–915 g / sq m)
<b>Grain</b>	Full
<b>Grain Texture</b>	Smooth, tight
<b>Tannage</b>	Combination
<b>Dye</b>	Aniline
<b>Finish</b>	Naked
<b>Primary Uses</b>	Upholstery, handrails, wall panels, architectural applications
<b>Industry</b>	Contract, hospitality, marine, residential
<b>Maintenance</b>	Wipe entire surface with a soft cloth and cool water to even out any abrasions or stains. Do not spot rub, for it will darken only that area. Occasional use of Spinneybeck Aniline Leather Cleaner, Conditioner & Protector is recommended. Other leather cleaners such as saddle soap or household cleaners that may contain harsh chemicals, alcohol or ink removers should never be used.
<b>Custom</b>	Custom colors not available
<b>Special Services</b>	Perforated and embossed available with an upcharge
<b>Variation</b>	Color variation of naked leathers may be more pronounced beyond the normal commercial range. A Cutting for Approval (CFA) is required for all orders.
<b>Colorfastness to Light</b>	Class 2–3
<b>Colorfastness to Crocking</b>	Class 2–3 (dry)
<b>Flammability</b>	CAL 117: Pass CAL 133: Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent Cigarette Ignition Resistance NFPA 260: Class 1
<b>Durability + Strength</b>	Abrasion ASTM D 7255: n/a Breaking Force ASTM D 2208: 200 lb Elongation ASTM D 2211: 30–50% at 50 lb Flex ASTM D 2097: n/a Tearing Strength ASTM D 4705: 25 lb

**Standard Colors**

